Physical properties, Mechanical properties, Heat treatment, and Micro structure

This page is mainly introduced the SA-29 Grade 4027 chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of SA-29 Grade 4027, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## **Data Table for Grades Stainless Steels SA-29 Grade 4027**

	SA-29 Grade 4027 Standard Number:			
ITEM	Standard Number	Descriptions		
1	SA-29/SA-29M	Specification for Steel Bars, Carbon and Alloy, Hot-Wrought, General Requirements for		

SA-29 Grade 4027 Chemical composition(mass fraction)(wt.%)				
Chemical	Min.(%)	Max.(%)		
С		0.01		
Si		0.20		
Mn		0.30		
Р				
S				
Ni		0.15		
Cr	28.00	30.00		
Al				
Cu		0.15		
Τi				
Fe				
N		0.02		
Мо	3.50	4.20		

SA-29 Grade 4027 Physical Properties				
Tensile strength	115-234	σb/MPa		
Yield Strength	23	σ 0.2 ≥/MPa		
Elongation	65	δ5≥ (%)		
Ψ	-	ψ≥ (%)		
Akv	-	Akv≥/J		

Email: sales@tool-die-steels.com http://www.tool-die-steels.com/ Page 1 / 3

## SA-29 Grade 4027 Chemical information, Mechanical prope

Physical properties, Mechanical properties, Heat treatment, and Micro structure

HBS	123-321	-
HRC	30	-

SA-29 Grade 4027 Mechanical Properties				
Tensile strength	231-231	σb/MPa		
Yield Strength	154	σ 0.2 ≥/MPa		
Elongation	56	δ5≥(%)		
Ψ	-	ψ≥(%)		
Akv	-	Akv≥/J		
HBS	235-268	-		
HRC	30	-		

SA-29 Grade 4027 Heat Treatment Regime				
Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

SA-29 Grade 4027 Range of products				
Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED

## We can produce Stainless Steels the specifications follows:

Note:

- (1) listed in the table apex diameter (d), to steel thickness (a) multiples said.
- (2) in the ASTM A6 standard specified scope can meet any additional conditions.
- (3) from the standard for 50 mm (2 in).

Mechanical properties

Mechanische Eigenschaften

Caracteristiques mecaniques

ReH Minimum yield strength / Mindestwert der oberen Streckgrenze / Limite d'elasticite minimale

Email: sales@tool-die-steels.com http://www.tool-die-steels.com/ Page 2 / 3

## SA-29 Grade 4027 Chemical information, Mechanical prope

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Rm Tensile strength / Zugfestigkeit / Resistance a la traction

A Minimum elongation / Mindestwert der Bruchdehnung / Allongement minimal

J Notch impact test / Kerbschlagbiegeversuch / Essai de flexion par choc

Round bar:

Diameter: 1mm-2000mm

Square bar:

Size: 50mm \* 50mm-600mm \*600mm

Plate steel/flat bar:

Size: Thickness: 0.1mm-800mm Width: 10mm to 1500mm

Tube/pipe:

Size: OD: 6-219mm WT: 1-35 mm.

Cold-rolled sheet: Thickness: 2-5mm Width:1000mm Length: 2000mm

Hot-rolled sheet: Thickness:6-80mm Width: 210-610mm

Length: We can supply any length based on the customer's requirement.

Forging/hot rolling/ extrusion of steel.

Forging: Shafts with flanks/pipes/tubes/slugs/donuts/cubes/other shapes

Finished goods condition: hot forging/hot rolling + annealing/normalizing + tempering/quenching + tempering/any

conditions based on the customer's requirement

Surface conditions: scaled (hot working finish)/ground/rough machining/fine machining/based on the customer's requirement

Furnaces for metallurgical processing: electrode arc + LF/VD/VOD/ESR/Vacuum consumable electrode.

Ultrasonic inspection: 100% ultrasonic inspection for any inperfections or based on the customer's requirement.

UTS according to SEP 1921 C/c,D/d,E/e;A388 or GB/T 6402

Excellent service for all kinds of industries, with advantages of technologies, equipment and price.

We serve you with our honesty, integrity, and professionality.

Email: sales@tool-die-steels.com http://www.tool-die-steels.com/ Page 3 / 3